

Water Displacing Solvent Based Formulations

	E-Tec 501	E-Tec 503	E-Tec 504	E-Tec 505	E-Tec 505+
Film Characteristic	slightly oily	very slightly oily	dry to the touch	dry to the touch	dry, soft, non-tacky
Humidity Test (ASTM-D-1748)	35 days	35 days	35 days	25 days	35 days
Salt Spray Test (ASTM-B117)	72-96 hours	48 hours	48 hours	18-24 hours	96+ hours
Corrosion Test (Mil-C-23411)	pass	pass	pass	pass	pass
Corrosion Test (Mil-C-81309)	pass	pass	pass	pass	pass
Water Displacement (Mil-C-16173D, Grade 3)	pass	pass	pass	pass	pass
Stain Test (Mil-C-22235A)	pass	pass	pass	pass	pass
Approximate Coverage sq.ft./gallon	2,200	2,000	3,000	3,400	3,400
Approximate Film Thickness-dip	0.19 mil	0.12 mil	0.05 mil	0.03 mil	0.10 mil
Flash Point T.O.C.	126°	126°	125°	120°	130°
Weight per gallon, pounds	6.72	6.61	6.59	6.47	6.48